PATENT ABSTRACTS OF JAPAN

(11)Publication number:

2000-182671

(43)Date of publication of application: 30.06.2000

(51)Int.CI.

HO1M 10/40 HO1M 4/02 HO1M 4/48 HO1M 4/58

(21)Application number: 10-353145

(71)Applicant: FUJI PHOTO FILM CO LTD

(22)Date of filing:

11.12.1998

(72)Inventor: MAEKAWA YUKIO


NAKAMURA SHIGERU

(54) NON-AQUEOUS SECONDARY BATTERY

(57)Abstract:

PROBLEM TO BE SOLVED: To provide a non-aqueous secondary battery excellent in the over- charging safety, free of the risk of liquid leak, capable of operating at room temp., and suppressing dendritic growth of lithium metal during charging and discharging.

SOLUTION: A non-aqueous secondary battery is equipped with a negative electrode sheet 13 containing a negative electrode material capable of occluding and releasing lithium, a positive electrode sheet 11 containing a positive electrode active material, and a non-aqueous electrolyte, characterized by that, a) the positive electrode active material consists of a metal oxide or metal sulfide containing at least one of the vanadium, copper, iron, titanium, molybdenum and chromium and not substantially containing previously any lithium committing itself to the charge and discharge, b) a metal foil chiefly containing lithium is affixed previously to the negative electrode sheet, and c) the non-aqueous electrolyte is of gel form containing organic



aqueous electrolyte is of gel form containing organic polymer, aprotic solvent and ammonium salt or alkali metal or alkali earth metal salt.

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision ...

of rejection] [Date of requesting appeal against examiner's decision of rejection] [Date of extinction of right]

Copyright (C); 1998,2003 Japan Patent Office